

Dimensions – Sheet material

Standard Format

SHEET THICKNESS IN MM	SHEET WIDTH IN MM	SHEET LENGTH IN MM
3	930	3000 *
4	1350	3000 *
6	760	2490
6	910	2490 *
6	1350	3680*
9	760	3680
9	910	3680 *
9	1350	3680 *
12	760	3680
12	910	3680 *
12	1350	3680 *
12	1520	3680 *
19	760	3680 *

Special Format

SHEET THICKNESS IN MM	SHEET WIDTH IN MM	SHEET LENGTH IN MM
6	910	2490 **
9	910	3680 **
12	910	3680 **
19	760	3680 ***

* Only available in S028 Alpine White.

** Only available in S006 Arctic White.

*** Only available in Solid colours.

Special format available on special request, minimum quantities apply.

Size matters – to increase efficiency and reduce offcuts

HI-MACS® can be supplied in different sheet thicknesses, formats and sizes. Ideal for maximum cutting, minimum wastage and minimal costs. However, not all colours are available in all thicknesses. Please see the colour charts on the following pages for exact availability.

HI-MACS® fire resistant quality significantly widens the fields of application

HI-MACS® FR-version sheets are available in S728 Alpine White and manufactured to order in S801 Nougat Cream, S729 Ivory White, S706 Arctic White and S705 Grey.

Sheets in S728 Alpine White are especially suitable for use in public buildings, external facades and in the marine industry.

Chemical resistance

HI-MACS® is a fully homogenous material with no pores and is thus simple and easy to clean.

TEST SUBSTANCE	APPLICATION TIME	EVALUATION OF G02 CHANGES	EVALUATION OF S06 CHANGES
Acetic acid	16h	no change	no change
Citric acid	16h	no change	no change
Sodium carbonate	16h	no change	no change
Ammonium hydroxide	16h	no change	no change
Ethyl alcohol	16h	no change	no change
White wine, red wine	16h	no change	no change
Cola drinks	16h	no change	no change
Instant coffee	16h	no change	no change
Black Tea	16h	no change	no change
Blackcurrant juice	16h	no change	no change
Cream	16h	no change	no change
Water	16h	no change	no change
Petrol	16h	no change	no change
Acetone	16h	3	3
Ethyl butyl acetate	16h	3	3
Butter	16h	no change	no change
Olive Oil	16h	no change	no change
Mustard	16h	no change	no change
Salt	16h	no change	no change
Onions	16h	no change	no change
Lipstick	16h	no change	no change
Common household disinfectant	16h	no change	no change
Black pen – ballpoint	16h	2	2 – 3
Stamping ink	16h	1	1
Cleaning agent	16h	no change	no change
Cleaning solution	16h	no change	no change
Wear resistance group according to DIN 68861*	16h	1B	1B
Evaluation according to DIN 68930 Table 1 Other work surfaces: wear resistance group: «1C»		Requirement met +	according to DIN 68861 & DIN 68930

* 1A = Excellent; 1F = very bad 0 = no visible result; 5 = damaged